



BROWN ANTIQUE



BROWN ANTIQUE CLASSIC



BROWN ANTIQUE COHIBA

Massa volumica apparente	2697 kg/m ³
Resistenza alla flessione (EN 12372:2007)	9,8 MPa
Assorbimento (EN 13755:2008)	0,1%
Resistenza alla compressione (EN 1926:2007)	164 MPa
Porosità (EN 1936:2007)	0,13%
Resistenza all'abrasione (EN 14157:2005)	17,3 mm



SOLMAR