

CALACATTA CARRARA BORGHINI



Density	2719 kg/m ³
Absorption (average)	0.05%
Average dynamic coefficient of friction	0.84
Average Flexural strength (wet condition)	11.6 Mpa
Average Flexural strength (dry condition)	12.9 Mpa
Abrasion resistance (average)	56.9
Origin	Italy



SOLMAR