

# VALENTINE RED

EXCLUSIVE STONE by CMP SOLMAR



Petrographic classification (prEN 12407)	Biocrimita Filaments
Water absorption by weight – Imbition (UNE 22182)	0,10%
Apparent density (UNE 22182)	2.7 g/cm <sup>3</sup>
Open porosity (PE.02)	0.27%
Compressive break load before and after freezing - Loss of mass test after 25 cycles (UNE 22184)	0.04%
Strength after compression – Tensile strength (UNE 22185)	133,9 MPa
Strength to bending – Elasticity/bend resistance (UNE 22186)	8,5 MPa
Hardness – Knoop scale (UNE 22188)	1497,8 MPa
Shock-impact resistance (UNE 22189)	22,5 cm
Thermal dilatability (UNE 22197)	0.02%
Origin	Spain



SOLMAR